

# Rolled sheets

EN AW-5754 H111; EN 573-3; EN 485-2,-4

## Limit deviations of thickness according to EN 485-4

Specified thickness [mm]		Limit deviations of the thickness for the specified width [mm]				
over	to and include	to and include 1 000	over 1 000 to and include 1 250	over 1 250 to and include 1 600	over 1 600 to and include 2 000	over 2 000 to and include 2 500
0,5	0,6	±0,04	±0,06	±0,07	±0,08	±0,11
0,6	0,8	±0,04	±0,07	±0,08	±0,09	±0,12
0,8	1,0	±0,05	±0,08	±0,09	±0,10	±0,13
1,0	1,2	±0,05	±0,09	±0,10	±0,12	±0,14
1,2	1,5	±0,07	±0,11	±0,12	±0,14	±0,16
1,5	1,8	±0,08	±0,12	±0,13	±0,15	±0,17
1,8	2,0	±0,09	±0,13	±0,14	±0,16	±0,19
2,0	2,5	±0,10	±0,14	±0,15	±0,17	±0,20
2,5	3,0	±0,11	±0,15	±0,17	±0,19	±0,23
3,0	3,5	±0,12	±0,17	±0,19	±0,20	±0,24
3,5	4,0	±0,15	±0,20	±0,22	±0,23	±0,25
4,0	5,0	±0,18	±0,22	±0,24	±0,25	±0,29
5,0	6,0	±0,20	±0,24	±0,25	±0,26	±0,32

## Mechanical properties according to EN 485-2+A1

Material condition	Determined thickness [mm]		Tensile strength R <sub>m</sub> [Mpa]		Slip limit R <sub>p0,2</sub> [Mpa]		Ductility min. [%]		Bend radius		Hardness [HBW] <sup>o</sup>
	over	to	min.	max	min.	max	A <sub>50 mm</sub>	A	180°	90°	
H111	0,5	1,5	190	240	80		14		0,5 t	0,5 t	52
H111	1,5	3,0	190	240	80		16		1,0 t	1,0 t	52
H111	3,0	6,0	190	240	80		18		1,0 t	1,0 t	52

## Chemical composition according to EN 573-3 (AlMg3)

Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Other individually	Others in total	Al min.
0,4	0,4	0,1	0,5	2,6-3,5	0,3	-	0,2	0,15	0,05	0,15	Residue

## Formats in stock [mm] (\*)

1000 × 2000	1250 × 2500	1500 × 3000	-
-------------	-------------	-------------	---

(\*) Consult the sales department for the current availability of formats

## Thicknesses in stock [mm]

0,80 1,00 1,20 1,50 1,60 2,00 2,50 3,00 4,00 5,00 6,00
--

## Contact with foodstuffs according to EN 602

Yes
-----