

Square extruded bars

EN AW-6082 T6/T6511; EN 573-3; EN 755-2,-4

Limit deviations of thickness according to EN 755-4

Nominal thickness [mm]		Limit deviations of the thickness [mm]
18	25	±0,25
25	40	±0,30
40	50	±0,35
50	65	±0,40
65	80	±0,45
80	100	±0,55
100	120	±0,65
120	150	±0,80
150	180	±1,00
180	220	±1,15

Mechanical properties according to EN 755-2

Material condition	Nominal thickness [mm]		Tensile strength R_m [Mpa]		Slip limit $R_{p0,2}$ [Mpa]		Ductility min. [%]		Hardness [HBW]
	over	to	min.	max	min.	max	A_{50mm}	A	
T6/T6511	15	20	295	-	250	-	6	8	95
T6/T6511	20	150	310	-	260	-	-	8	95
T6/T6511	150	200	280	-	240	-	-	6	95
T6/T6511	200	250	270	-	200	-	-	6	95

Chemical composition according to EN 573-3 (AlSiMgMn)

Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Other individually	Others in total	Al min.
0,7-1,3	0,5	0,1	0,4-1	0,6-1,2	0,25	-	0,2	0,1	0,05	0,15	Residue

Lengths in stock [mm] (*)

3000	and other
------	-----------

Thickness in stock [mm]

20 25 30 35 40 45 50 55 60 65 70 80 90 100 110 120 130 140 150
--

Contact with foodstuffs according to EN 602

Yes
